

EGprime A6002/B6002 System

EGprime A6002/B6002 system is a high ultraviolet resistivity transparent liquid type epoxy compound what developed for encapsulation of electronic devices, especially for light emitting diodes (LED).

1. COMPOSITION

Component 1: A6002 (Resin)
Component 2: B6002 (Hardener)

2. FEATURES

- ⊙ High Ultraviolet Resistivity
- ⊙ Good Pot Life
- ⊙ Elevated Temperature Color Stability
- ⊙ Excellent Electrical Properties
- ⊙ Exceptional Optical Transmission
- ⊙ Good Solvent Resistance
- ⊙ High Reliability

3. PROPERTIES BEFORE CURED

3.1 Appearance & Color

| | Resin A6002 | Hardener B6002 |
|------------------|-------------------|----------------------------|
| Appearance | Blue tinged grade | Colorless to slight yellow |
| Color (Gardener) | — | 1 max. |

3.2 Specific Gravity

Measure at 25±1℃

| | Resin A6002 | Hardener B6002 |
|------------------|-------------|----------------|
| Specific gravity | 1.16±0.05 | 1.16±0.05 |

3.3 Viscosity

Measure condition: Brookfield RV at 25±1℃

A6002: spindle 21/2.5 rpm

B6002: spindle 21/100 rpm

| | Resin A6002 | Hardener B6002 |
|-----------------|-------------|----------------|
| Viscosity (cps) | 3700(TYP.) | 500 (TYP.) |

4. MIXING INSTRUCTION

4.1 Mix Ratio (Select applicable for your products.):

A6002 (Resin) : B6002 (Hardener) = 100 : 100

- ☆ Mix ratio of these materials is fixed by their chemistry. Any attempt to increase or decrease the cure rate by adding more or less hardener will result in degraded materials.

4.2 Pot-life

4hrs at 25℃ (500g mass)

5. PROCESSING SERIES

| | |
|---------------|--|
| PreProcessing | Component A to be preheated at 60°C /30 min. If preheating for long is necessary, please don't heat up the material at 60 over 8 hrs. |
| Mixing | The mixture of resin (A)/hardener (B)/diffusant and colorant Paste may be mixed using standard techniques. |
| Defoam | Use vacuum device; 0~10 mm Hg |
| Casting | Filling the mixture in to the molds with small nozzles. |
| Curing | 120°C×1.5hrs or 130°C×1hrs depending on the oven device. (Select applicable for your products.) |
| Demolding | — |
| Post cure | 140 deg. C or 150 deg. C in 6hrs ~ 8 hrs |

6. PROPERTIES OF CURED PRODUCT

CURED CONDITION: METHOD① cure at 130°C 1hr + 150°C 6hrs (5 mm)

METHOD② cure at 20°C/min. to 250°C (depend on the DSC)

6.1 TESTING METHOD

| ITEM | TEST METHOD | SAMPLE SIZE |
|--|--|---|
| Glass Transition Temperature | DuPont 2910 DSC & DuPont 2940 TMA & DuPont 2100 TA Sy. | ①7±3 mg for DSC ②40±0.1 mg for DSC 1.9±0.2mm(thickness) for TMA |
| Heat Distortion Temperature | ASTM D 648 | 12.7 ×12.7 ×127 distance of supports 101.6mm |
| Flexural Strength | ASTM D 790 | 12.7(W) ×6.4(H)mm |
| Impact Strength | ASTM D 256 | 2.7 ×12.7 ×63.5mm |
| Durometer Hardness | ASTM D 2240 | 4 mm thickness |
| Chemical Resistance | ASTM D 543 | 76.2 ×25.4 ×3.2mm |
| Coefficient of linear expansion | TA Q400 TMA | 1.9 mm (thickness) |
| Volume & Surface Resistivity (500 V) | ASTM D 257 | 50 (Φ)×2 mm |
| Boiling water absorption | JIS K 6911 | 120°C / 2 atm 100 hrs |
| Dielectrical Cnostant & Dissipation Factor | ASTM D 150 | — |

6.2 PHYSICAL PROPERTIES

| ITEM | UNITS | MEASURING CONDITION | ANALYTICAL VALUE |
|---------------------------------|---------------------|----------------------|--|
| Glass Transition Temperature | °C | 30~250°C 20°C/min | Mixr atio:A:B=100:100 Method ①135±10 ②135 ± 10 |
| Heat Distortion Temperature | °C | — | Mix ratio: A:B=100:100 157 ± 10 |
| Flexural Strength | kg/ mm ² | 23°C | 11 |
| Impact Strength | | 23°C | 7 |
| Durometer Hardness | — | 25°C | >85 |
| Coefficient of linear expansion | μ m/m °C | 30~100°C | 7E-5±2E-5 |
| Refractive Index | — | — | 1.53±0.01 |
| Boiling water absorption | wt% | 120°C/2atm 100hrs | < 2.2 |
| Light Transmittance | — | 400~700nm | 90% (min.) |

6.3 ELECTRIC PROPERTIES

| ITEM | UNITS | MEASURING CONDITION | ANALYTICAL VALUE |
|---------------------------------|-------|---------------------|----------------------|
| Dielectrical Constant (10 K Hz) | — | 25°C | 3.0 |
| | | 100°C | 3.1 |
| | | 120°C | 3.1 |
| Dissipation Factor (10 K Hz) | — | 25°C | 0.011 |
| | | 100°C | 0.006 |
| | | 120°C | 0.006 |
| Surface Resistivity | Ω | 25°C | 6.3×10 ¹⁵ |
| Volume Resistivity | Ω -cm | 25°C | ≥ 1×10 ¹⁵ |

7.ITEMS OF Q.C. REPORT

- ⊙ Resin Viscosity
- ⊙ Hardener Viscosity
- ⊙ Weight loss of Resin (TGA)
- ⊙ Weight loss of Hardener (TGA)
- ⊙ Glass Transition Temperature of Cured Product

8.PACKING

A6002 4 kgs in plastic container or can.
B6002 4 kgs in plastic container or can.

Content of Label

- ⊙ DESC
- ⊙ Lot No.
- ⊙ Net weight
- ⊙ Expiry Date
- ⊙ Manufacture Date

9.SHELF LIFE

6 months(from the date of manufacture) @ at 10~30°C, under 70%RH, factory sealed containers.

10.NOTICE OF STORAGE

1. Keep components A and B at 10~30°C, factory sealed containers.
2. Store in cool dry place away from strong oxidizing agents, acids and bases.
3. Crystallization is unlikely to happen with component A, In case of crystallization please heat up the material at 60°C for 2 hour followed by well agitation.

SAFETY AND HANDLING

Avoid eye and skin contact with resin A and curing agent B. In case of accidental skin contact, wash immediately with soap and water to remove.

Waterless hand cleaners may be used if followed immediately by thoroughly washing with soap and water.

In case any of these materials gets into the eyes, flush eyes thoroughly with low-pressure water for 15 minutes and obtain medical attention.